



JC07 Rec'd PCT/PTO 19 MAR 2002 TS

10/088406

TRANSMITTAL LETTER TO THE UNITED STATES PATENT & TRADEMARK OFFICE ATTORNEY'S DOCKET NUMBER 50778

DESIGNATED/ELECTED OFFICE (DO/EO/US)  
CONCERNING A FILING UNDER 35 U.S.C. 371

U.S. APPLICATION NO. (If known, see 37 CFR 1.5)

| INTERNATIONAL APPLICATION NO. | INTERNATIONAL FILING DATE | PRIORITY DATE CLAIMED |
|-------------------------------|---------------------------|-----------------------|
| PCT/EP00/09020                | 15 September 2000         | 1 October 1999        |

TITLE OF INVENTION: ACTIVATION OF PASSIVATED IRON

APPLICANT(S) FOR DO/EO/US Frank OHLBACH, Rolf FISCHER, Hermann LUYKEN, Johann-Peter MELDER,  
Martin MERGER, Andreas ANSMANN, Peter BASSLER

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. /X/ This is a FIRST submission of items concerning a filing under 35 U.S.C. 371.
2. / / This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371.
3. /X/ This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. /x/ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. /X/ A copy of the International Application as filed (35 U.S.C. 371(c)(2)).
  - a./X/ is transmitted herewith (required only if not transmitted by the International Bureau).
  - b./ / has been transmitted by the International Bureau.
  - c./ / is not required, as the application was filed in the United States Receiving Office (RO/USO).
6. /X/ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. /X / Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)).
  - a./X / are transmitted herewith (required only if not transmitted by the International Bureau).
  - b./ / have been transmitted by the International Bureau.
  - c./ / have not been made; however, the time limit for making such amendments has NOT expired.
  - d./ / have not been made and will not be made.
8. /X / A translation of the amendments to the claims under PCT Article 19(35 U.S.C. 371(c)(3)).
9. /x / An oath or declaration of the inventor(s)(35 U.S.C. 171(c)(4)).
- 10./ / A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11. to 16. below concern other document(s) or information included:

- 11./X/ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
- 12./x/ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
- 13.x / A FIRST preliminary amendment.  
/ / A SECOND or SUBSEQUENT preliminary amendment.
- 14./ / A substitute specification.
- 15./ / A change of power of attorney and/or address letter.
- 16.x / Other items or information.  
International Search Report  
International Preliminary Examination Report

20040909

10/088406

JC10 Rec'd PCT/PTO 19 MAR 2002

U.S. Appl. No. (If Known) INTERNATIONAL APPLN. NO.  
PCT/EP00/09020ATTORNEY'S DOCKET NO.  
50778

|                                                                                                                                                                       |                     | CALCULATIONS        | PTO USE ONLY |
|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------|---------------------|--------------|
| 17. /X/ The following fees are submitted                                                                                                                              |                     |                     |              |
| BASIC NATIONAL FEE (37 CFR 1.492(a)(1)-(5)):                                                                                                                          |                     |                     |              |
| Search Report has been prepared by the EPO or JPO.....                                                                                                                | \$890.00            | 890.00              |              |
| International preliminary examination fee paid to USPTO (37 CFR 1.482).....                                                                                           | \$710.00            |                     |              |
| No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.445(a)(2)).....                        | \$740.00            |                     |              |
| Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO .....                                | \$1,040.00          |                     |              |
| International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(2)-(4).....                              | \$100.00            |                     |              |
| <b>ENTER APPROPRIATE BASIC FEE AMOUNT = \$</b>                                                                                                                        |                     | 890.00              |              |
| Surcharge of \$130.00 for furnishing the oath or declaration later than / / 20 / / 30 months from the earliest claimed priority date (37 CFR 1.492(e)).               |                     |                     |              |
| <u>Claims</u>                                                                                                                                                         | <u>Number Filed</u> | <u>Number Extra</u> | <u>Rate</u>  |
| Total Claims                                                                                                                                                          | 4 -20               |                     | X\$18.       |
| Indep. Claims                                                                                                                                                         | 1 -3                |                     | X\$84.       |
| Multiple dependent claim(s) (if applicable)                                                                                                                           |                     |                     | +280.        |
| <b>TOTAL OF ABOVE CALCULATION</b>                                                                                                                                     |                     | <b>= 890.</b>       |              |
| Reduction of 1/2 for filing by small entity, if applicable. Verified Small Entity statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28).                         |                     |                     |              |
| <b>SUBTOTAL</b>                                                                                                                                                       |                     | <b>= 890.</b>       |              |
| Processing fee of \$130. for furnishing the English translation later than / / 20 / / 30 months from the earliest claimed priority date (37 CFR 1.492(f)).            |                     |                     |              |
| <b>TOTAL NATIONAL FEE</b>                                                                                                                                             |                     | <b>= 890 .</b>      |              |
| Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) \$40.00 per property |                     |                     |              |
| <b>TOTAL FEES ENCLOSED</b>                                                                                                                                            |                     | <b>= \$ 930.00</b>  |              |
| Amount to be refunded:                                                                                                                                                |                     | \$                  |              |
| Charged                                                                                                                                                               |                     | \$                  |              |

a./X/ A check in the amount of \$ 930.00 to cover the above fees is enclosed.

b./ / Please charge my Deposit Account No. \_\_\_\_\_ in the amount of \$ \_\_\_\_\_ to cover the above fees. A duplicate copy of this sheet is enclosed.

c./X/ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 11-0345. A duplicate copy of this sheet is enclosed.**NOTE:** Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.**SEND ALL CORRESPONDENCE TO:**KEIL & WEINKAUF  
1101 Connecticut Ave., N.W.  
Washington, D. C. 20036

SIGNATURE

Herbert B. Keil

NAME

Registration No. 18,967

2005 FEB 24 09:48:00

10/088406

JC10 Rec'd PCT/PTO 19 MAR 2002

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re the Application of )  
OHLBACH et al. ) BOX PCT  
)  
International Application )  
PCT/EP 00/09020 )  
)  
Filed: September 15, 2000 )  
)

For: ACTIVATION OF PASSIVATED IRON

PRELIMINARY AMENDMENT

Honorable Commissioner of  
Patents and Trademarks  
Washington, D.C. 20231

Sir:

Prior to examination, kindly amend the above-identified application as follows:

IN THE CLAIMS

Kindly amend the claims as shown on the attached sheets.

R E M A R K S

The claims have been amended to eliminate multiple dependency and to place them in better form for U.S. filing. No new matter is included.

A clean copy of the claims is attached.

Favorable action is solicited.

Respectfully submitted,

KEIL & WEINKAUF



Herbert B. Keil  
Reg. No. 18,967

1101 Connecticut Ave., N.W.  
Washington, D.C. 20036

(202)659-0100

205 FEB 20 2002

CLEAN VERSION OF AMENDED CLAIMS - OZ 50778

3. A process as claimed in claim 1, wherein the nitrile used is an aliphatic nitrile.
4. A process as claimed in claim 1, wherein the nitrile used is a compound selected from the group consisting of adiponitrile and 6-aminocapronitrile.

2016-04-20 10:40:00

MARKED VERSION OF AMENDED CLAIMS - OZ 50778

3. A process as claimed in claim 1 [or 2], wherein the nitrile used is an aliphatic nitrile.
4. A process as claimed in claim 1 [any of claims 1 to 3], wherein the nitrile used is a compound selected from the group consisting of adiponitrile and 6-aminocapronitrile.

2067E0" 90439001

CLAIMS AS FILED - OZ 50778

1. A process for high pressure hydrogen activation of passivated iron useful as catalytically active component after said activation, which comprises effecting said activation in the presence of a nitrile at from 20 to 180°C.
2. A process as claimed in claim 1, wherein said activation is effected at from 2 to 40 MPa.
3. A process as claimed in claim 1, wherein the nitrile used is an aliphatic nitrile.
4. A process as claimed in claim 1, wherein the nitrile used is a compound selected from the group consisting of adiponitrile and 6-aminocapronitrile.

206750 30488007

JC10 Rec'd PST/PTC 19 MAR 2002

## Activation of passivated iron

## Description

5

The present invention relates to a process for high temperature, high pressure hydrogen activation of passivated iron useful as catalytically active component after said activation, which comprises effecting said activation in the presence of a nitrile at from 20 to 180°C.

Catalysts consisting wholly or substantially of elemental iron are very important, for example for the synthesis of ammonia from nitrogen and hydrogen, for producing hydrocarbons from synthesis gas (Fischer-Tropsch synthesis) and for the hydrogenation of nitriles to amines (J.W. Geus, Applied Catalysis 25, 313 - 333 (1986)).

Such catalysts are usually prepared by reducing iron oxides with hydrogen. To this end, the iron oxide is reduced in a hydrogen stream at high temperatures, the oxide oxygen being converted into water and removed in that form.

DP patent 855,263 describes the reduction of molten and subsequently comminuted iron oxide at 400°C in a hydrogen stream.

J. Mater. Sci. Lett. 8 (8) (1989), 895 - 898 reports the experimental finding that the complete reduction of iron oxides to iron in a hydrogen stream can only be achieved at temperatures above 400°C and that the reduction of doped iron oxides as used in ammonia synthesis can be achieved only at above 500°C.

US 3,758,584 discloses at column 1 lines 47 to 65 reducing iron oxides at 300 to 600°C in the presence of 0.01 to 10 percent by volume of ammonia. Preference is given to a temperature of 350 to 420°C, in which case the hydrogen contains 0.25 - 3 percent by volume of ammonia (column 2 lines 12 - 18). Such iron catalysts are used for example for hydrogenating adiponitrile to hexamethylenediamine.

40

According to US 4,480,051, the reduction can also be carried out in three stages by reducing the iron oxide with hydrogen or mixtures of hydrogen and ammonia in a first step, then treating the resulting elemental iron with an oxygen-containing gas in a second step and then as third step repeating the reduction similarly to the first step.

The reduced iron catalyst obtained according to the processes mentioned is pyrophoric. If the reduction of the iron oxide was carried out directly in the synthesis reactor contemplated for the later reaction, the catalyst can subsequently be used for the contemplated chemical reaction. However, the reduction in the synthesis reactor has disadvantages: since the reduction together with the heating and cooling takes many hours, the reactor is unavailable for manufacture during this period. In addition, the reduction temperature can be distinctly above the later synthesis temperature. So the reactor has to be overengineered because of the reduction.

It can therefore be advantageous to reduce the iron oxide outside the contemplated synthesis reactor. However, the pyrophoric catalyst has to be passivated by treatment with air in order that it may be transported to the synthesis reactor and installed.

According to WO 98/11059, this passivation may be effected with nitrogen-oxygen mixtures at temperatures from 20 to 80°C, preferably 25 to 60°C. The activation of such catalysts ("reduced/passivated") is then effected in the synthesis reactor in a hydrogen atmosphere at from 180 to 500°C, preferably from 200 to 400°C.

Activation for the purposes of the present invention is the conversion of reducedly [sic]/passivated iron into a catalytically active form.

The disadvantage is that even the subsequent activation in the reactor necessitates high temperatures in the range from 200 to 400°C. This leads to appreciable extra costs on account of the increased equipment needs (preheater, cycle gas compressor, reactor material, etc.). Also, although the time needed for the activation is less than with the initial reduction of the iron oxide, it is still high. For instance, A. V. Slack, G. R. James: Ammonia, Part II, Marcel Dekker Inc., 1977, 113 - 114 describes the procedure for activating a passivated iron used in ammonia synthesis. The activation takes place at from 300 to 480°C and takes about 17 hours, to which has to be added the same time for heating the reactor.

DE-A-3,524,330 describes the activation of passivated iron in the presence of a Redox system, eg ketone/alcohol, at temperatures of about 200°C. The disadvantages here are the high temperature and the appreciable time required for the activation.



## 3

It is an object of the present invention to provide a process for a technically simple and economical high temperature, high pressure hydrogen activation of passivated iron useful as catalytically active component after the activation without the 5 disadvantages mentioned.

We have found that this object is achieved by the process defined at the outset.

- 10 The passivated iron which is used in the process of the invention and which is useful as catalytically active component after the activation can be obtained according to processes known per se.

Useful precursors for such an iron accordingly include iron 15 oxides, iron hydroxides, iron oxyhydroxides or mixtures thereof (component a). Examples include iron(III) oxide, iron(II, III) oxide, iron(II) oxide, iron(II) hydroxide, iron(III) hydroxide or iron oxyhydroxide such as  $\text{FeOOH}$ . Synthetic or naturally occurring iron oxides, iron hydroxides or iron oxyhydroxides can be used, 20 such as magnetite, which has the idealized formula of  $\text{Fe}_3\text{O}_4$ , brown ironstone, which has the idealized formula of  $\text{Fe}_2\text{O}_3 \times \text{H}_2\text{O}$ , or red ironstone (hematite), which has the idealized formula of  $\text{Fe}_2\text{O}_3$ .

Such compounds can be used to produce supported iron catalysts, 25 but are preferably used for producing unsupported iron catalysts.

Useful precursors for such an iron include as component a) readily water-soluble salts of iron, such as nitrates, chlorides, acetates, formates or sulfates, preferably nitrates, or mixtures 30 thereof, and also mixtures of such salts with the aforementioned iron oxides, iron hydroxides or iron oxyhydroxides.

Such compounds can be used to produce unsupported iron catalysts, but are preferably used for producing supported iron catalysts. 35

The passivated iron which is used in the process of the invention and which is useful as catalytically active component after activation may include further components, such as promoters.

- 40 Advantageous promoters are one or more of the following elements or compounds based on the following elements or mixtures thereof (component (b)):

palladium, cobalt, ruthenium, rhodium, platinum, iridium, osmium, 45 copper, silver, gold, chromium, molybdenum, tungsten, manganese, rhenium, zinc, cadmium, lead, aluminum, tin, phosphorus, arsenic,

antimony, bismuth and rare earth metals, silicon, zirconium, vanadium, titanium.

- 5 Advantageous further components (component (c)) are one or more compounds based on one or more alkali or alkaline earth metals.

To prepare the passivated iron useful as catalytically active component after activation, the precursor of component (a) may

- 10 already contain component (b) or its precursors partially or completely. Similarly, to prepare the passivated iron useful as catalytically active component after activation the precursor of component (a) may already contain component (c) or its precursors partially or completely.

- 15 Preferred precursors for component (b) include readily water-soluble salts or complexes of the elements mentioned, such as nitrates, chlorides, acetates, formates, sulfates, preferably nitrates.

- 20 Preferred precursors for component (c) include readily water-soluble salts or complexes of the elements mentioned, such as hydroxides, carbonates, nitrates, chlorides, acetates, formates, sulfates, preferably hydroxides and carbonates.

- 25 Catalyst precursors including passivated iron useful as catalytically active component after activation with or without component (b) or (c) or components (b) and (c) are useful as precursors for supported or unsupported catalysts.

- 30 Such supported catalysts may include conventional carrier materials, preferably aluminum oxide, silicon oxide, aluminosilicates, lanthanum oxide, titanium dioxide, zirconium dioxide, magnesium oxide, zinc oxide, zeolites or activated

- 35 carbon and also mixtures thereof.

In a general embodiment for producing catalyst precursors, precursors of component (a) are precipitated if desired together with precursors of component (b) and if desired with precursors

- 40 of component (c) in the absence or, in the case of supported catalysts, in the presence of carrier materials, if desired the catalyst precursor thus obtained is processed into extrudates or tablets, dried and subsequently calcined.

The precipitation from generally aqueous solutions may be effected in a conventional manner, for example by addition of precipitating reagents, by changing the pH or by changing the temperature.

Supported catalysts are generally also obtainable by saturating a carrier material with a solution of component (a), if desired component (b) and if desired component (c), the individual components being added simultaneously or in succession, or by spraying the components (a), if desired component (b) and if desired component (c) onto a carrier material in a conventional manner.

The catalyst precursor material thus obtained may be predried in a conventional manner, generally at from 80 to 150°C, preferably at from 80 to 120°C.

This is generally followed by a calcination. The calcining is customarily effected at from 150 to 500°C, preferably at from 200 to 450°C, in a gas stream, for example an air stream or a nitrogen stream.

The catalyst precursors including passivated iron useful as catalytically active component after activation may also be obtained by melting iron-containing oxides, hydroxides or oxyhydroxides or mixtures of such compounds at above 1500°C. These iron-containing starting compounds may already include component (b) or component (c). It is similarly possible if desired to add component (b) or component (c) or components (b) and (c).

After calcination, the catalyst precursor material is generally exposed to a reducing atmosphere. This is preferably done by exposing the catalyst precursor material to a gas atmosphere containing molecular hydrogen and if desired further gases, especially inert gases, such as nitrogen, at from 200 to 500°C, preferably at from 250 to 450°C. The reaction times are generally within the range from 2 to 72 hours. The space velocity over the catalyst precursor in this operation is preferably in the range from 100 to 500 standard l/l of catalyst precursor x hour, the space velocity over the ammonia synthesis catalyst precursor is preferably in the range from 2000 to 10,000 standard l/l of catalyst precursor x hour.

The catalyst precursor including metallic iron is generally passivated at from 20 to 100°C, preferably at from 25 to 60°C. An advantageous way of doing this is to contact the catalyst

precursor with an oxidizing gas, preferably with a gas containing molecular oxygen, especially with a mixture of nitrogen and oxygen.

- 5 To prepare a passivated catalyst including iron useful as catalytically active component after activation, the invention provides that the catalyst precursor be activated with hydrogen at from 20 to 180°C and at elevated pressure in the presence of a nitrile.

10

The hydrogen may be used as pure gas or as a gas containing further constituents, such as inert gas, for example nitrogen or argon, especially nitrogen.

- 15 The activation of the catalyst precursor may be effected with advantage in the reactor in which the catalyst is used after activation. To this end, the catalyst precursor may be disposed as a fixed bed in the reactor or be suspended in the reactor in a solvent.

20

Useful nitriles include in principle all nitriles individually or mixed, ie organic compounds which contain at least one, preferably more than one, such as two, three or four, nitrile groups which are reactive in the process of the invention, such

- 25 as aromatic nitriles, ie nitriles in which the nitrile group is directly attached to an aromatic or arylaliphatic, for example benzonitrile, o-aminobenzonitrile or phthalonitrile, or aliphatic nitriles, ie nitriles in which the nitrile group is directly attached to an aliphatic system or to the aliphatic moiety of an

30 arylaliphatic.

The aromatic or aliphatic nitriles may bear one or more, such as two, three or four, further identical or different functional groups, such as amino groups or ester groups.

35

Useful aliphatic nitriles are aliphatic nitriles of from 1 to 20 carbon atoms, reckoned without the nitrile group or groups and with the aliphatic system being linear, branched or cyclic, such as linear nitriles having one nitrile group, for example

- 40 acetonitrile or propionitrile, cyclic nitriles having one nitrile group, for example cyclohexyl nitrile, linear nitriles having one nitrile group and a further functional group, for example cyanoacetic esters or 6-aminocapronitrile, such as linear nitriles having two nitrile groups, for example

45 2-methylglutaronitrile, adiponitrile or succinonitrile.

It will be appreciated that mixtures of a plurality of nitriles may also be used.

The preparation of such nitriles is known per se.

5

When the catalyst precursor is disposed as a fixed bed in a reactor, the activation may be carried out continuously or batchwise in downward or upward flow. According to the invention, the temperature is in the range from 20 to 180°C, especially from 30 to 150°C. The pressure should advantageously be in the range from 2 to 40 MPa, especially from 3 to 30 MPa.

10

The activation may preferably be carried out in the presence of an inorganic solvent, such as ammonia, or of an organic solvent, such as an amine, diamine or triamine, preferably of from 1 to 6 carbon atoms, for example trimethylamine, triethylamine, tri-n-propylamine, tri-i-propylamine, tributylamine, such as an alcohol, for example methanol, ethanol, n-propanol, i-propanol, n-butanol, i-butanol, s-butanol, preferably ammonia.

15

20

In a preferred embodiment, from 1 to 10 g, preferably from 2 to 6 g, of solvent, especially ammonia, may be used per g of nitrile.

25

The space velocity over the catalyst precursor is advantageously in the range from 0.1 to 2.0 kg, especially from 0.3 to 1.0 kg, of nitrile/l x h.

When the catalyst precursor is used in the form of a suspension in a solvent, the activation may be carried out batchwise or preferably continuously in the liquid phase in particular. The

30

temperature should advantageously be in the range from 20 to 180°C, preferably from 40 to 150°C, especially from 50 to 100°C. The pressure should advantageously be in the range from 2 to

35

40 MPa, preferably from 2 to 30 MPa, particularly preferably from 3 to 30 MPa, especially from 4 to 9 MPa. The residence time should advantageously be in the range from 50 to 275 min, preferably from 70 to 200 min.

The activation may preferably be carried out in the presence of an inorganic solvent, such as ammonia, or of an organic solvent, such as an amine, diamine or triamine, preferably of from 1 to 6 carbon atoms, for example trimethylamine, triethylamine, tri-n-propylamine, tri-i-propylamine, tributylamine, such as an alcohol, for example methanol, ethanol, n-propanol, i-propanol, n-butanol, i-butanol, s-butanol, preferably ammonia.

40

45

In a preferred embodiment, the nitrile concentration is in the range from 10 to 90% by weight, preferably from 30 to 80% by weight, especially from 40 to 70% by weight, based on the sum  
5 total of nitrile and solvent.

In a preferred embodiment, the amount of catalyst precursor, based on the amount of nitrile, is in the range from 1 to 50% by weight, especially from 5 to 20% by weight.

10

The nitriles used in the process of the invention are generally obtained partly as amines and partly as carboxamides after the activation.

15 The course of the activation may be followed in a conventional manner, for example by gas chromatographic analysis of the reaction effluent in the case of a continuous process or gas chromatographic analysis of samples of the reaction mixture in the case of a batchwise process.

20

Particularly advantageous catalytically active iron obtainable by the process according to the invention includes from 0 to 25% by weight of component (b), based on component (a), and from 0 to 10% by weight of component (c), based on component (a).

25

Optimum parameters for obtaining the desired composition are simple to determine in a few preliminary experiments.

The iron obtainable by the process according to the invention is  
30 useful in numerous chemical processes, for example the synthesis of ammonia from nitrogen and hydrogen, the production of hydrocarbons from synthesis gas (Fischer-Tropsch synthesis) or in hydrogenations, such as the hydrogenation of nitriles, especially alpha,omega-dinitriles to alpha,omega-aminonitriles or  
35 alpha,omega-diamines, as catalytically active component in heterogeneous catalysts.

The heterogeneous catalysts are preferably used in the hydrogenation of adiponitrile to hexamethylenediamine and the  
40 partial hydrogenation of adiponitrile to 6-aminocapronitrile and hexamethylenediamine.

If the catalyst is used for the synthesis of ammonia from nitrogen and hydrogen or for the production of hydrocarbons from  
45 synthesis gas (Fischer-Tropsch synthesis), the heterogeneous catalyst may, after activation, be advantageously washed with

10083406 "031902"

solvents, such as alcohols, hydrocarbons, amines, ammonia or ether, and if appropriate dried.

If the catalyst is used for the hydrogenation of nitriles, the nitrile to be reacted over the activated catalyst may advantageously be used during the activation in the process of the invention.

#### Example 1

10

All %ages in the example are by weight, unless otherwise stated.

#### a) Activation of reducedly passivated iron

15 The catalyst precursor was prepared by melting a magnetite ore in air at above 1550°C. The magnetite ore used had the following composition:

72% of Fe, 0.08% of Al, 0.03% of Ca, 0.05% of Mg, 0.12% of Si,  
20 0.01% of Ti, 0.17% of Mn, balance oxygen.

The cooled melt block was comminuted in a jaw crusher. A sieve fraction of particle size 1.5 - 3 mm was separated out by sieving and reduced in a hydrogen/nitrogen stream at 450°C in the course  
25 of 72 hours. After cooling down to room temperature under nitrogen, the catalyst was passivated with a mixture of 1% of air with nitrogen in the course of 24 hours, care being taken to ensure that the temperature of the bed hot spot did not exceed 45°C.

30

In a 270 ml autoclave, 80 g of reducedly [sic]/passivated catalyst spall was installed in a wire cage and the autoclave was sealed. 69 g of ammonia and 34.5 g of ACN were then introduced, the autoclave was heated to 110°C and hydrogen was pressed in via  
35 a 2000 rpm sparging stirrer to a total pressure of  $250 \times 10^5$  Pa. After about an hour, the hydrogen uptake started, the rate of uptake rising almost linearly with time until the nitriles had been completely converted. Samples were taken during the reaction, and it was determined that ACN is completely converted  
40 into HMD and ACSA (Tab. 1).

ACN = 6-aminocapronitrile

HMD = hexamethylenediamine

ACSA = 6-aminocaproamide

45 ADN = adiponitrile

Tab. 1

| Reaction time<br>(min) | ACN<br>(area %) | HMD<br>(area %) | ACSA<br>(area %) |
|------------------------|-----------------|-----------------|------------------|
| 70                     | 96.22           | 1.10            | 2.10             |
| 135                    | 61.02           | 30.93           | 6.92             |
| 195                    | 2.95            | 86.89           | 8.80             |
| 255                    | 0.54            | 89.36           | 8.76             |
| 360                    | 0.17            | 89.73           | 8.73             |

Table 1 shows that the water formed reacts with ACN to form ACSA.

b) Hydrogenation of adiponitrile to hexamethylenediamine

The catalyst prepared according to 1 a) by activation of reduced-passivated iron catalyst was used in the same reactor for hydrogenating adiponitrile to hexamethylenediamine. Unlike 1a), the reactor was operated continuously. The hydrogenation was carried out at 135°C,  $250 \times 10^5$  Pa and a catalyst space velocity of 1.0 kg of ADN/l of cat. x h. A mixture of ammonia and ADN in a weight ratio of 2 : 1 was fed into the reactor continuously. During a period of 100 hours samples were taken and analyzed by gas chromatography, revealing a hexamethylenediamine yield of 99% coupled with complete ADN conversion.



We claim:-

1. A process for high pressure hydrogen activation of passivated  
5 iron useful as catalytically active component after said  
activation, which comprises effecting said activation in the  
presence of a nitrile at from 20 to 180°C.
2. A process as claimed in claim 1, wherein said activation is  
10 effected at from 2 to 40 MPa.
3. A process as claimed claim 1 or 2, wherein the nitrile used  
is an aliphatic nitrile.
- 15 4. A process as claimed in any of claims 1 to 3, wherein the  
nitrile used is a compound selected from the group consisting  
of adiponitrile and 6-aminocapronitrile.

20

25

30

35

40

45

## Activation of passivated iron

## Abstract

5

A process for high temperature, high pressure hydrogen activation of passivated iron useful as catalytically active component after said activation comprises effecting said activation in the presence of a nitrile.

10

15

20

25

30

35

40

45

2025-03-04 10:05:05

# Declaration, Power of Attorney and Petition

Page 1 of 4

0050/050778

Customer No.



26474

PATENT & TRADEMARK OFFICE

We (I), the undersigned inventor(s), hereby declare(s) that:

My residence, post office address and citizenship are as stated below next to my name,

We (I) believe that we are (I am) the original, first, and joint (sole) inventor(s) of the subject matter which is claimed and for which a patent is sought on the invention entitled

## ACTIVATION OF PASSIVATED IRON

the specification of which

☒ is attached hereto.

☐ was filed on \_\_\_\_\_ as

Application Serial No. \_\_\_\_\_

and amended on \_\_\_\_\_.

☒ was filed as PCT international application

Number PCT/EP/00/09020 \_\_\_\_\_

on 15 September 2000 \_\_\_\_\_,

and was amended under PCT Article 19

on \_\_\_\_\_ (if applicable).

We (I) hereby state that we (I) have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

We (I) acknowledge the duty to disclose information known to be material to the patentability of this application as defined in Section 1.56 of Title 37 Code of Federal Regulations.

We (I) hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed. Prior Foreign Application(s)

| Application No. | Country | Day/Month/Year  | Priority Claimed                                                    |
|-----------------|---------|-----------------|---------------------------------------------------------------------|
| 19947508.3      | Germany | 01 October 1999 | <input checked="" type="checkbox"/> Yes <input type="checkbox"/> No |

pluspet001 - 25

We (I) hereby claim the benefit under Title 35, United States Codes, § 119(e) of any United States provisional application(s) listed below.

|                      |               |
|----------------------|---------------|
| _____                | _____         |
| (Application Number) | (Filing Date) |
| _____                | _____         |
| (Application Number) | (Filing Date) |

We (I) hereby claim the benefit under 35 U.S.C. § 120 of any United States application(s), or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. § 112, I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application.

| Application Serial No. | Filing Date | Status (pending, patented, abandoned) |
|------------------------|-------------|---------------------------------------|
| _____                  | _____       | _____                                 |
| _____                  | _____       | _____                                 |
| _____                  | _____       | _____                                 |

And we (I) hereby appoint **HERBERT. B. KEIL**, Registration Number 18,967; and **RUSSEL E. WEINKAUF**, Registration Number 18,495; the address of both being Messrs. Keil & Weinkauf, 1101 Connecticut Ave., N.W., Washington, D.C. 20036 (telephone 202-659-0100), our attorneys, with full power of substitution and revocation, to prosecute this application, to make alterations and amendments therein, to sign the drawings, to receive the patent, and to transact all business in the Patent Office connected therewith.

We (I) declare that all statements made herein of our (my) own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

Declaration

Page 3 of 4

0050/050778

1-00  
Frank Ohlbach  
NAME OF INVENTOR

Frank Ohlbach  
Signature of Inventor

Date October 5, 2000

Schulstr.7  
69221 Dossenheim DEX  
Germany  
Citizen of: Germany  
Post Office Address: same as residence

2-00  
Rolf Fischer  
NAME OF INVENTOR

Rolf Fischer  
Signature of Inventor

Date October 5, 2000

Bergstr.98  
69121 Heidelberg DEX  
Germany  
Citizen of: Germany  
Post Office Address: same as residence

3-00  
Hermann Luyken  
NAME OF INVENTOR

Hermann Luyken  
Signature of Inventor

Date October 5, 2000

Brüsseler Ring 34  
67069 Ludwigshafen DEX  
Germany  
Citizen of: Germany  
Post Office Address: same as residence

4-00  
Johann-Peter Melder  
NAME OF INVENTOR

Johann-Peter Melder  
Signature of Inventor

Date October 5, 2000

Fichtenstraße 2  
67459 Böhl-Iggelheim DEX  
Germany  
Citizen of: Germany  
Post Office Address: same as residence

Declaration

Page 4 of 4

0050/050778

5-00  
Martin Merger

NAME OF INVENTOR

Martin Merger

Signature of Inventor

Date October 5, 2000

Max-Slevogt-Str.25

67227 Frankenthal

Germany

Citizen of: Germany

Post Office Address: same as residence

DE X

6-00  
Andreas Ansmann

NAME OF INVENTOR

Andreas Ansmann

Signature of Inventor

Date October 5, 2000

Im Köpfle 6

69168 Wiesloch

Germany

Citizen of: Germany

Post Office Address: same as residence

DE X

7-00  
Peter Baßler

NAME OF INVENTOR

Peter Baßler

Signature of Inventor

Date October 5, 2000

Maria-Mandel-Str.18

68519 Viernheim

Germany

Citizen of: Germany

Post Office Address: same as residence

DE X